

TRANSFLOW S3™ VACUUM

The only choice for phthalate-free flexible tubing

Dairy and Vacuum Applications

Transflow S3™ Vacuum from Saint-Gobain Performance Plastics is now phthalate-free. Saint-Gobain is proud to be among the first companies to offer sustainable flexible tubing products. The bio-based Transflow S3™ line combines the high performance standards customers demand with an eco-friendly tubing design.

Reduced Maintenance and Inspection Concerns

Transflow S3™ Vacuum tubing is ideally suited for supply air transport. The smooth inner surface is less susceptible to particle entrapment, which can restrict air flow, while crystal clarity permits detection of equipment deficiencies such as backflow of milk into the air lines. Transflow S3™ Vacuum tubing is designed to work in tandem with Transflow S3™ M-34-R to provide a vacuum tube and easy fluid flow within the milking process.

The Mark of Quality

Every foot of Transflow S3™ Vacuum Tubing has been embedded with a trademark blue stripe within the tubing walls. The embedded blue stripe is your assurance of receiving genuine Transflow® tubing, the world's finest raw milk tubing produced specifically for the dairy industry.

Regulatory Standards

Transflow S3™ complies with FDA, NSF, 3-A and Japan Food Sanitation Law # 370/1959 for many foods and beverages. Transflow S3™ tubing products do not contain chemicals listed in California's Prop 65.

* The compliance status of Transflow S3™ Vacuum according to the marketing region can be found on www.TygonS3.com. Please refer to the detailed document of compliance for a complete compliance information and appropriate use instruction. The complete compliance information and use instructions can be found at www.TygonS3.com.



Transflow S3™ VACUUM A24 and A24-C Features/Benefits

- Holds full vacuum at room temperature
- Will not crack and age like rubber tubing
- Lightweight and flexible for quick installation
- Non-wetting properties allow easy cleaning and complete drainage
- Durability for long and reliable service
- Contains no BPA or phthalates
- To be used in conjunction with Transflow S3™ M-34-R

Typical Applications

- Raw milk transport lines*
- Dairy processing*

Relative chemical resistance properties for Transflow S3™ Vacuum A-24 and A-24-C*

Acids			Bases			Salts	Alcohols	Ketones
Conc.	Med.	Weak	Conc.	Med.	Weak			
F	E	E	F	E	E	E	F	U

E = Excellent F = Fair U = Unsatisfactory
 *All tests conducted at room temperature.

Product Characteristics

Opacity	A-24 A-24-C	Clear Opaque
FDA Compliant for Food Contact		Yes
NSF 51 Standard		No
USP Class VI		No

Tubing Properties

3,175mm ID x 6,35mm OD	—
Minimum Bend Radius, mm	28,57
Max. Working Pressure @ 23°C, bars	1,7
Vacuum Rating @ 23°C, mm Hg	759,5

Typical Physical Properties

Property	ASTM Method	Value or Rating
Durometer Hardness (Shore A), 15 Sec	D2240	56
Tensile Strength, MPa	D412	12,1
Ultimate Elongation, %	D412	425
Tear Resistance, kN/m	D1004	31
Specific Gravity	D792	1,21
Water Absorption, % 24 hrs. @ 23°C	D570	0,21
Compression Set Constant Deflection, % @ 70°C for 22 hrs.	D395 Method B	64
Brittleness Temp., °C	D746	-36
Maximum Recommended Operating Temp. °C	-	74
Tensile Stress @ 100% Elongation, MPa	-	4,0
Tensile Set, %	D412	95
Color	A-24 A-24-C	Clear Black

Unless otherwise noted, all tests were conducted at room temperature (23°C). Values shown were determined on 1,905mm thick extruded strip or 1,905mm thick molded ASTM plaques or molded ASTM durometer buttons.

Transflow S3™ Cleaning Instructions

To extend the usable life of Transflow S3™ tubing and reduce the risk of bacterial growth resulting from a buildup of milksoil film, the following cleaning and sanitary procedures must be followed:

- Following milking and dumping, rinse tubing with clean water at 43°C without recirculating until discharge is clear.
- Wash tubing with alkaline cleaner (containing no caustic soda) for 10-15 minutes at 65°C; final dump temperature should not be below 46°C.
- Use an acid rinse to prevent milkstone deposits.
 - Perform daily after each cleaning for 5 minutes with cold- to room-temperature water.
 - Perform a once-weekly acid rinse for 15 minutes with 43°C - 60°C water in place of the alkaline cleaner used in Step 2 above.
- Purge moisture by draining and passing warm filtered air through the tubing until complete dryness is achieved.
- Sanitize tubing immediately prior to use following the manufacturer's recommended procedures.

The values listed for working and burst pressures are derived from tests conducted under controlled laboratory conditions. Many factors will reduce the tubing's ability to withstand pressures, including temperature, chemical attack, stress, pulsation and the attachment to fittings. It is imperative that the user conduct tests simulating the conditions of the application prior to specifying the tubing for use.

TRANSFLOW S3™ VACUUM TUBING IS NOT INTENDED FOR USE AS AN IMPLANT MATERIAL.



Saint-Gobain Performance Plastics

2664 Gilchrist Road Tel: (800) 798-1554
 Akron, OH 44305 Tel: (330) 798-9240
 Fax: (330) 798-6968

Transflow® is a registered trademark.



IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain Performance Plastics tubing for all intended uses. Laboratory and clinical tests must be conducted in accordance with applicable regulatory requirements in order to determine the safety and effectiveness for use of tubing in any particular application.

For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product to be free from defects in materials and workmanship. Our only obligation will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risk, if any, including the risk of injury, loss or damage, direct or consequential, arising out of the use, misuse, or inability to use, this product. THIS WARRANTY IS IN LIEU OF THE WARRANTIES OF MERCHANTABILITY, FITNESS FOR PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED. No deviation is authorized.

Saint-Gobain Performance Plastics Corporation assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to those products. All such advice is given and accepted at the buyer's risk.